RESEARCH ARTICLE

Physical and anatomical variations in culm characteristics of *Pseudoxytenanthera bourdillonii* (Gamble) H.B.Naithani – a lesser studied endemic bamboo in the Western Ghats, Kerala

Krishnapriya K. R.^{1*}. Sreekumar V. B². Syam Viswanath³

Received: 24 January 2024/Accepted: 25 June 2024 Published online 29 April 2025

Abstract: Pseudoxytenanthera bourdillonii (Gamble) H.B.Naithani, locally known as "Arayambu", represents one of the lesser-known bamboo species in the Western Ghats region of Kerala (restricted to Palakkad, Thrissur, Idukki and Malappuram districts). The present study evaluated physical and anatomical properties of this species including fibre characters across various culm height. Experimental methods outlined in IS 6874 (2008) were used for moisture content and basic density studies. Franklin method was adopted for fibre maceration. It was observed that the moisture content consistently showed a decreasing trend from bottom to top whereas the basic density found a reverse trend. The plant volumetric shrinkage reaches its peak in the middle of the culm. The highest fibre length (2.65 \pm 0.16 mm) was noticed in the middle slivers taken from the bottom portion of culm. The fibre width and lumen width of the bottom part showed a significant difference compared to middle and top culm (P < 0.05). There was no significant difference in wall thickness between height position and radial position. The average Runkel ratio found to be greater than one. Vascular bundle numbers showed an increasing trend from

- ² Department of Forest Botany KSCSTE-Kerala Forest Research Institute Peechi, Kerala, India
- ³ Former Director KSCSTE-Kerala Forest Research Institute Peechi, Kerala, India ⊠ syam.viswanath@gmail.com

bottom to top. Additionally, the vessel diameter was higher in inner compared to middle and outer part. There was a significant difference in parenchyma diameter between outer and inner portion. Despite having a runkel ratio greater than one, other fibre parameters of *P. bourdillonii* make it suitable for pulping and remains a favorable option for handicraft sector owing to its non-thorny nature substantial intermodal length, and attractive golden yellow color of both the culm and culm sheath. However, *P. bourdillonii* culms of two-year age group is less preferred for high strength demanding purpose due to high moisture content and lower basic density.

Keywords: P. bourdillonii, fibre characteristics, Runkel ratio, culm physical properties

Introduction

Non-Timber Forest Products (NTFPs) play a crucial role in sustaining livelihood for 80% of the world's population, meeting essential needs like livestock support, fuelwood, furniture etc. (Charlotte et al., 2021). For centuries, bamboo has served as a socially and economically significant non-timber forest product, meeting the daily needs of millions of people across widely distributed tropical and subtropical regions (Ahmad et al., 2021; Lobovikov et al., 2004).With higher potential productivity, rapid growth and ease of propagation, bamboo emerges as a promising alternative to traditional wood resources, positioning itself as a significant non wood forest asset. (Zhan et al., 2015). The continuous progress in technology has significantly amplified the potential application of bamboo, with nearly 4000 commercial products crafted from this versatile material now being utilized on a global scale (Singh, 2008). Globally, bamboo forest

^{*}Corresponding Authors

¹ Department of Forest Botany KSCSTE- Kerala Forest Research Institute, Peechi, Kerala, India

span a vast expanse of 36 million hectares, with India accounting for 16 million hectares, followed by China with 6.5 million hectares, and Brazil with 4 million hectares. The international trade value of bamboo was pegged at 68.8 billion USD in 2018, significantly influencing the lives of 2.5 billion people directly or indirectly worldwide (FSI, 2019; INBAR, 2019).

Bamboo stands out as a viable alternative to the diminishing resources of forest timber. Non-woody plants, including bamboo, offer various advantages, such as rapid growth cycles, quick maturation, modest requirements for irrigation and fertilization, and a low lignin content. The latter characteristic is particularly significant as it contributes to a reduction in the energy and chemicals needed during the pulping process, making bamboo a sustainable and environmentally friendly option for various industrial applications (Navaee-Ardeh et al., 2004). Bamboo species, with their distinct properties, emerge as valuable alternatives in the realm of pulp and paper industry. The increasing demand for wood and fibre, and the low availability of traditional wood supplies, have prompted researchers to actively seek non wood plants possessing fibre properties comparable to those of wood (Worku et al., 2023).

However, there are still some underexploited and lesser known endemic bamboo species, which if studied and properly utilized could bring about a significant change in productivity and end use patterns. *P. bourdillonii* (Fig.1). stand out as underutilized and least studied bamboo resources in Kerala, holding immense potential for exploration and development. *P. bourdillonii* is endemic to Kerala regions of western Ghats locally referred to as "arayambu". This species thrives in the challenging terrain of steep precipices and wet rocks within moist deciduous forests flourishing at altitudes ranging from 750 -1300 meters. This species is prized by local indigenous tribes for its easy workability and attractive shiny nature of end products in traditional handicrafts. The other versatile applications of this bamboo include using its culms for crafting toothpicks, creation of honey bottles, and basketry, while the culm sheath finds its purpose in the production of various handicrafts (Seethalakshmi *et al.*, 1998; Kumar, 2009). The mature culms are also favoured in farm and house construction by indigenous tribes in Nelliampathy, Palakkad in Kerala.

Understanding the properties of Bamboo is crucial, as they vary significantly between species and even within the culm of the same plant. Comprehensive studies of different bamboo species are essential to ascertain their suitability for specific end uses. Morphological characters play a pivotal role in this assessment. Moreover, physical properties such as moisture content, basic density, and hollowness are key determinants of bamboo strength and its appropriateness for diverse applications. These factors collectively contribute to the overall performance and durability of bamboo in various contexts, ranging from construction to crafts and other industrial uses. Therefore, a thorough investigation into these morphological and physical characteristics is indispensable for informed decision-making in utilizing bamboo effectively and sustainably (Selvan et al., 2017).



Fig 1. Natural distribution of P. bourdillonii in Nelliampathy (A), Culm of P. bourdillonii (B)



Fig 2. Study sites of P. bourdillonii

The literature review revealed comprehensive information on the morphology, occurrence and revisionary studies of the selected species. However, there is a significant lack of research addressing fundamental aspects like physical properties and anatomical properties of, *P. bourdillonii* to date. Thus, this study aims to evaluate the anatomical and physical properties of *P. bourdillonii* across different culm heights and locations, aiming to contribute valuable information that enhances potential applications of these species.

Materials and methods

Culm samples of *P. bourdillonii* were methodically collected from five distinct locations (Fig. 2) which includes two different locations in Chimmini Cheriya Ponmudi Thrissur (N 10° 31' 12.6" E 076° 21' 24.0"), (N10°25'53.3" E 076° 31'19.0"),vicinity of Valanjanganam waterfall in Kuttikkanam (N 09° 33' 45.15" E 076° 58' 40.20") Seetharkunde areas in Nelliampathy (N 10° 33' 05.17" E 076° 42' 20.01") and from KFRI-FRC Palapilly bambusetum (N 10° 26' 10.6" E 076° 21' 36.6").

The two-year-old culms were randomly collected from these sites ensuring a cutting height above 30 cm to prevent hindrance to the growth of remaining culms. The harvested culms are subsequently divided into bottom, middle, and top portions.

Physical properties

P. bourdillonii is a moderate sized, straggling bamboo forming open clumps. Culms reach a height of 15-20 m height with a diameter of 8-10 cm at the base, tapering to 2-4cm. The average internodal length at the base of harvested culms is 50 - 60 cm.

Moisture content

Three centimetres long round culms representing five sites and three culm heights (base, middle, and top) were cut from freshculms to determine its initial moisture content. The green weight of each specimen was measured using an analytical balance with a 0.01g accuracy (IS 6874, 2008). The specimens were then oven-dried at a temperature of (103 ± 2) °C until attaining constant weight. The moisture content was calculated using Equation

Moisture content =
$$\frac{\text{GW} - \text{ODW}}{\text{ODW}} \times 100\%$$

where GW is the green weight (the weight of the sample before drying), OD W is the weight of the specimen after drying in oven up to constant weight (Oven dried weight).

Basic density

Three centimeters long specimens, (representing 5 sites and three culm heights), were cut from fresh culms of *P. bourdillonii* used for the determination of basic density. The green weights of all specimens were measured using an analytical balance with an accuracy of 0.01 g. The water displacement method was used to determine the volume of each specimen. The specimens were then oven-dried at a temperature of (103 ± 2) °C. The repeated measurement of weight was recorded until the constant weight was reached. Basic density was determined based on IS 6874 (2008). Basic density was calculated using the equation

Basic density =
$$\frac{\text{OD weight (g)}}{\text{Green volume (cm}^3)}$$

Volumetric shrinkage

Specimens each 3-cm in length and representing five distinct site of the species at three different culm height were initially measured for green volume using water displacement method. Subsequently, the specimen underwent oven drying at a controlled temperature of (103 ± 2) °C until a constant weight was achieved with the final measurement recorded as oven dried volume. The determination of shrinkage followed by the standards outlined in ASTM D 143-94 (1990) and Razak, 2012. The shrinkage was calculated using the equation

Volumetric shrinkage =
$$\frac{\text{GV - ODV}}{\text{GV}} \times 100\%$$

Where GV is the green volume (the volume of the sample before drying), ODV is the volume of the specimen after drying in oven (Oven dried volume)

Anatomy assessment

The bamboo culms were divided into bottom, middle and top portions. The fixation process involves Formalin -acetic acid (FAA) composed of 90% ethanol (conc. 70%), 4% glacial acetic acid, and 6% Formaldehyde (conc. 37-48%) was applied immediately after felling the specimen blocks. These were subsequently stored in sealed containers, preserving them for further anatomical observations (Razak, 1998).

Observation on anatomical features

The observations focus primarily on key anatomical features including number of vascular bundles, meta

xylem vessel size, fibres, parenchyma diameter and parenchyma lumen width. These investigations adhered to the methodologies established by Jane,1933; Abdul Latif and Mohd Tamizi, 1992. Bamboo sample blocks were cut into sections of 10 mm \times 10 mm \times culms wall thickness sliced into 25 µm thick transverse sections by sledge microtome with a 15-degree knife angle. Each section was stained with 4 drops of aqueous safranin. They were washed with 50% ethanol then dehydrated through alcohol series of 70, 80, 90 and 95%, and 3 changes of absolute ethanol for 1 minute. Observations were based on three replicate slides. Cell measurements were done using Leica image analyser.

Number of vascular bundles, meta xylem vessel size, parenchyma diameter and parenchyma lumen width were measured in outer middle and inner regions of bottom middle and top sections. The distributions of vascular bundles were determined by counting the number of vascular bundle on a cross-section per mm².

Maceration process

Match size Samples prepared separately from outer, middle inner slivers of bottom, middle and top portions using a sharp knife. The splints were subsequently placed in a marked vial, and an equal volume (1:1) of 10% glacial acetic acid and 30% Hydrogen Peroxide (H₂O₂) was added. The mixture subjected to boiling at 100±2°c until the splints achieved a softened and bleached white state following the maceration protocol adopted by Franklin, 1945. At the end of the maceration period, the softened splints will be carefully washed with distilled water. Subsequently the vials were half filled with distilled water and securely capped. Drops of safranin were introduced to contrast the fibre's images.

Fibre dimension Measurements

The fibre dimensions measured include fibre length, fibre diameter, and lumen diameter. 2.5x magnification used to measure fibre length while other dimensions determined using 40x magnification. Fibre double wall thickness obtained from the difference between fibre diameter and lumen diameter. Twenty-five complete and reasonably straight fibres was measured.

Derived morphological fibre characteristics:

i Runkel Ratio/ = <u>2 x cell wall thickness</u> Rigidity Coefficient Lumen width

11	Slenderness ratio /Felting Coefficient /Aspect ratio =	Fibre length Fibre width

iii Flexibility Ratio/ Elasticity Coefficient = $\frac{\text{Lumen width}}{\text{Fibre width}}$

Statistical analysis

..

For each sample, 25 readings were taken from inner, outer, and middle slivers of the bottom, middle and top portions to measure fibre morphology. More than three replications from each location were used to measure physical properties such as moisture content, density, and volumetric shrinkage. The average results with SD are reported in the manuscript. A 95% confidence limit of P value less than or equal to 0.05 was used to determine significance. Twoway ANOVA followed by the least significant difference test as post hoc analysis was done for comparing each parameter between height position and between radial position.

Result and Discussions

Moisture content

The present study examined moisture content of *P. bourdillonii* by analysing samples from 5 different locations and assessing variation in moisture level at bottom, middle and top positions of 2-year-old culms. The mean moisture content obtained from five different siteswas $160.60 \pm 84.72\%$. The moisture content decreases progressively from the base to the top of the culm as its height increases. The bottom portion exhibits highest moisture content

175.79 \pm 73.32% followed by the middle 171.05 \pm 98.43% and 135.55 \pm 79.15% in the top. Statistical analysis reveals no significant variation (p>0.05) indicating that the position of the culm does not significantly influence the moisture content. This moisture content is higher than 133% recorded at the bottom of *B. balcooa* (Kamruzzaman *et al.*, 2008). The decrease in moisture content aligned with prior observation in other bamboo species indicating a consistent trend as the culm height increased (Wahab *et al.*, 2009). Conversely, the decline in the initial moisture content could be attributed to a lower proportion of vascular bundles at the base compared to the upper section of the culm (Anokye *et al.*, 2014).

Basic density

The average basic density was 0.45 ± 0.14 g/cm³. The average basic density of P. bourdillonii is lower than B. balcooa (0.595 g/cm³) (Kamruzzaman et al., 2008). Contrary to moisture content, the basic density exhibited a upward trend with values of 0.424 \pm 0.117 g/cm^3 , $0.447 \pm 0.154 \text{ g/cm}^3$, $0.485 \pm 0.153 \text{ g/cm}^3$ observed from the base to top (Fig. 3). Several researchers have documented trends consistent with this study, observing rise in basic density as the height of the culm increases from base to top (Wahab et al., 2009; Vetter et al., 2015). No significant variation was observed along the culm height (p>0.05). Typically, density in bamboo falls within the range of approximately 0.4 - 0.9 g/cm³, a variation influenced by its anatomical structure, as indicated by the quantity and distribution of fibres around the vascular bundles (Mussa et al., 2023).



Fig 3. Average physical property values of *P. bourdillonii*; error bars represent mean standard deviation; MC-moisture content (%), BD –basic density (kg/m³),VS- volumetric shrinkage (%).

Variable	Bottom	Middle	Тор	F-value(P-value)
Green weight	$79.60^{a} + 24.31$	$33.70^{b} + 9.5$	$9.12^{\circ} + 4.13$	142.6**(<0.001)
Oven- dried weight	$29.12^{a} + 7.49$	$13.27^{b} + 4.09$	$3.92^{\circ} + 1.53$	167.2**(<0.001)
Green volume	$73.67^{a} + 24.27$	$31.58^{b} + 9.58$	$8.91^{\circ} + 4.31$	120.2**(<0.001)
Oven-dried volume	$39.17^{a} + 11.55$	$17.08^{b} + 5.12$	$5.23^{\circ} + 1.94$	141.1**(<0.001)
Moisture content	175.79 + 73.32	171.05 + 98.43	135.55 + 79.15	1.747 ^{ns} (0.181)
Basic density	0.424 + 0.117	0.447 + 0.154	0.485 ± 0.153	1.207 ^{ns} (0.305)
Volumetric Shrinkage	43.05 + 16.81	43.09 + 17.18	35.71 + 17.28	1.598 ^{ns} (0.209)

 Table 1. Comparison of different physical parameters in P. bourdillonii between bottom, middle and top portion of culm

** Significant at 0.01 level; ns non-significant Means having different small letter as superscript differ significantly within a raw

Volumetric shrinkage

The mean value of volumetric shrinkage of *P. bourdillonii* is 40.59 \pm 17.11 %. with the highest peak value observed in the middle of the culm having average value 43.09 \pm 17.18%. The bottom and middle part showed relatively similar values with the bottom recorded 43.05 \pm 16.81%. Lowest volumetric shrinkage at the top 35.71 \pm 17.28%. The identified pattern previously reported in Iron bamboo (*Guadua angustifolia*), where a lower volumetric shrinkage consistently observed in the top of culm (Villareal *et al.*, 2020). There was no significant variation in volumetric shrinkage along culm height.

The variation in shrinkage could be attributed to the anatomical structure of the culm, where the inner portion comprise more parenchyma cells but fewer fibres and conducting cells compare to the outer portion of the culm (Wahab *et al.*, 2010). The higher moisture content in the inner tissue induces increased stress and collapse, resulting in the greater shrinkage

as observed (Anokye *et al.*, 2014). Table 1 represents physical parameters of *P. bourdillonii* across various culm heights.

Anatomical properties of P. bourdillonii

The culm tissue comprised of two cell types parenchyma and vascular bundles. In the bamboo culm approximately 50% composed of parenchyma, 40% fibres, and 10% vessels and sieve tubes (Maye *et al.*, 2013; Liese 1998). Vascular bundle type IV with combination of Type III is found in *P. bourdillonii* (Fig. 4 & 5). Basal internodes show type IV, middle - combination of type IV and III and top parts showing Type III bundles. Vasular bundle type IV consist of two isolated fibre strand at the phloem and protoxylem side. Besides the central strand Type III has a separate fibre strand. Type IV predominantly occurs in basal internodes where additional support is often required and is provided by two fibre bundles (Liese, 1998).



Fig 4. Type IV vascular bundle in the Bottom of *P. bourdillonii* - 2.5x magnification (A), Single vascular bundle having two isolated fibre strands -10x magnification (B)



Fig 5. Type III vascular bundles in the top of *P. bourdillonii* - 6.3x magnification (A) & (B).





Fig 6. Fibre length of *P. bourdillonii* – 2.5x magnification





Fig 8. Average fibre parameter values of *P. bourdillonii*; error bars represent mean standard deviation; FL-fibre length,(mm) FW–fibre width(μ m), FLU- fibre lumen (μ m), DWT- double wall thickness(μ m), WT- wall thickness(μ m), RR-runkel ratio.

Fibre morphology

Characterized by a slender form, the fibres exhibit a length that is elongated and tapered at both ends, occasionally featured forked structures. The overall strength of the culm and its pulping properties are directly influenced by the length of the fibres (Liese, 1998). The characteristics of fibre stand out as a pivotal variable in assessing appropriateness as raw material for pulp and paper production (Kayama,1979). Fig 6 & 7 illustrates fibre morphology of *P. bourdillonii*. The mean fibre parameter values are shown in Fig 8.

Fibre length

International Association of Wood Anatomists (IAWA) classifies fibres into three groups: mediumlength (0.91-1.60 mm), moderately long (1.61-2.20 mm) and very long (2.21-3.00 mm) (Adi *et al.*, 2014). The mean fibre length of *P. bourdillonii* is 2.32 ± 0.08 mm categorises the plant as long fibre plant. Longer fibre length enhances the tearing resistance of paper (Sharma *et al.*, 2011). This fibre length is higher than *Ochlandra travancorica* (2.20mm) (Azzini and Zalgado, 1982), and *Bambusa vulgaris* (2.10mm) (Sadiku *et al.*, 2016).

The largest mean fibre length is found at the middle slivers of bottom part, and shortest fibres at the outer slivers of middle part. There is no significant difference in fibre length of bottom, middle and top part. However, a significant variation seen in fibre length of outer and middle parts, with the middle part exhibiting the highest average value 2.55 ± 0.10 mm (Table 2). There is no significant difference in the fibre length of middle and inner parts. The interaction between height position and radial position found to be statistically non-significant.

Table 2. Results of comparison of fibre length between height position and between radial position in *P. bourdillonii*

TT. '- 1.4'4'			0			
Height position	Outer	Middle	Inner	Overall		
Bottom	1.99 ± 0.32	2.65 ± 0.16	2.55 ± 0.25	2.40 ± 0.16		
Middle	1.65 ± 0.13	2.62 ± 0.14	2.62 ± 0.21	2.30 ± 0.15		
Тор	2.11 ± 0.19	2.38 ± 0.21	2.35 ± 0.20	2.28 ± 0.11		
Overall	$1.92^{\text{b}}\pm0.13$	$2.55^{\text{a}}\pm0.10$	$2.51^{a}\pm0.12$	2.32 ± 0.08		
Between F-value Height position = 0.267 ns; P-value = 0.767 Between F-value radial position = 8.64 **; P-value = 0.001 Interaction between height position and radial position = 1.007 ns; P-value = 0.417						

** Significant at 0.01 level; ns non-significant Means having different small letter as superscript differ significantly within a raw

	Onenall				
Height position	Outer	Middle	Inner	- Overall	
Bottom	17.53 ± 2.03	18.09 ± 0.79	18.01 ± 0.66	$17.88^{\rm A}\pm0.71$	
Middle	13.89 ± 1.35	16.08 ± 0.95	16.68 ± 1.21	$15.55^{\mathrm{B}}\pm0.71$	
Тор	14.82 ± 1.01	16.44 ± 0.28	14.30 ± 0.53	$15.19^{\mathrm{B}}\pm0.44$	
Overall	15.41 ± 0.91	16.87 ± 0.46	16.33 ± 0.61	16.20 ± 0.40	

Table 3. Results of comparison of fibre width between height position and between radial position

Between F-value Height position = 5.334^{**} ; P-value = 0.009Between F-value radial position = 1.355ns; P-value = 0.271Interaction between height position and radial position = 0.777ns; P-value = 0.548

** Significant at 0.01 level; ns non-significant Means having different capital letter as superscript differ significantly within a column.

Height position		Quarall		
reight position -	Outer	Middle	Inner	– Overali
Bottom	9.14 ± 1.67	10.61 ± 1.27	10.68 ± 1.52	$10.14^{\rm A}\pm0.82$
Middle	6.26 ± 1.44	7.70 ± 1.35	7.57 ± 1.83	$7.17^{\rm B}\pm0.85$
Тор	4.89 ± 1.20	6.49 ± 1.35	4.71 ± 0.51	$5.36^{\rm B}\pm0.62$
Overall	$\boldsymbol{6.76 \pm 0.91}$	8.27 ± 0.85	7.65 ± 0.99	7.56 ± 0.53
	0.70 ± 0.91	0.27 ± 0.00	1.00 ± 0.99	1: 1

Table 4. Results of comparison of fibre lumen between height position and between radial position

Between F-value Height position = 8.989^{**} ; P-value = 0.001Between F-value radial position = 0.884ns; P-value = 0.422Interaction between height position and radial position = 0.165ns; P-value = 0.955

** Significant at 0.01 level; ns non-significant; Means having different capital letter as superscript differ significantly within a column.

Fibre width

The average fibre width of P. bourdillonii is found to be 16.20 ± 0.40 µm. The highest fibre width was found in the middle slivers of bottom position with an average value $18.09 \pm 0.79 \ \mu\text{m}$. The shortest fibre width found in the inner position of the top part 14.30 ± 0.53 µm. The fibre width of the bottom part vary significantly with the fibre width of middle and top positions (p < 0.05), there is no significant difference in fibre width at the outer middle and inner parts ($p \ge$ 0.05), (Table 3). This overall fibre width of P. bourdillonii surpasses that of various bamboo species such as Bambusa vulgaris (14.8 µm) as reported by Egbewole et al.(2015), as well as Gigantochloa apus (14.5µm) reported by Sugesty et al. (2015), and even exceeds the measurements observed in the hardwood of Melia azedarach (13.45 µm) as reported by Megra et al. (2022).

Fibre lumen Diameter

The highest lumen diameter of *P. bourdillonii* was obtained from the inner slivers of the bottom part with an average value $10.68 \pm 1.52 \ \mu\text{m}$. The shortest lumen found at the inner slivers of top position is $4.71 \pm 0.51 \ \mu\text{m}$. The average value of fibre lumen diameter of *P. bourdillonii* is $7.56 \pm 0.53 \ \mu\text{m}$. *P. bourdillonii* exhibits higher fibre lumen width compared to several other bamboo species *Dendrocalamus strictus* ($4.33 \ \mu\text{m}$), *D.latiflorus* ($3.44 \ \mu\text{m}$), *D. giganteus* ($5.66 \ \mu\text{m}$), *D. asper* ($3.97 \ \mu\text{m}$), *B. vulgaris*

(3.81µm), and *B. beecheyana* (3.55µm) (Rusch *et al.*, 2021). The width of the fibre lumen plays a crucial role in the pulp beating process, with a larger lumen contributing to improved beating efficiency. This is due to the enhanced penetration of the liquids in to the fibre lumen, facilitating more effective pulp treatment (Sharma *et al.*, 2011). The fibre lumen width of bottom 10.14 ± 0.82 µm varies significantly with that of middle7.17 \pm 0.85 µm and top 5.36 \pm 0.62 µm (p<0.05)- Table 4. But the fibre lumen diameter of outer, middle and inner slivers not differ statistically.

Double wall thickness

Double wall thickness determined by subtracting fibre diameter with lumen diameter. The average double wall thickness of *P. bourdillonii* is found to be $8.64 \pm 0.47 \mu m$. The highest double wall thickness found in the middle part of the top of culm 9.95 $\pm 1.45 \mu m$. There is no significant difference of double wall thickness between height positions and radial positions (Table 5).

Wall thickness

The average fibre wall thickness of *P. bourdillonii* is $4.32 \pm 0.23 \ \mu\text{m}$. The thickest wall found in the outer slivers of top of the culm $4.96 \pm 0.46 \ \mu\text{m}$ while the thinnest at the inner slivers of bottom position $3.67 \pm 0.82 \ \mu\text{m}$. Wall thickness increases form bottom to top. The difference in wall thickness between the height position and radial position is not statistically

significant (Table 6). The wall thickness of *P. bourdillonii* is lower than *B. vulgaris* (5.06µm), *Ochlandra travancorica* (6.00µm), and *D. asper* (5.69µm). *A. donax*, which has been utilized as an excellent raw material for producing handmade paper, has a cell wall thickness of 5.36µm. Plants having thinner cell walls contribute to the production of high-quality paper (Boadu *et al* 2020). The wall thickness of *P. bourdillonii* is slightly higher than *Eucalytus* sp.with 3.29-3.86 µm (Viane *et al.*, 2009), and is comparable to *G. scortechinii* 4.3 µm (Razak *et al.*, 2012)

Fibre derived values of P. bourdillonii

Runkel ratio

The runkel ratio of different height position is $1.19 \pm$

0.25 in bottom $1.96\pm$ 0.41 in the middle and top having 2.66 ± 0.34 . The average runkel ratio of P. *bourdillonii* is 1.93 ± 0.21 . There is no significant difference in the outer middle and inner slivers. Runkel ratio of top and bottom vary significantly (p<0.05) (Table 7). If the runkel ratio is less than 1 it is more suitable for paper making Xu et al., 2006. Bottom part of P. boudillonii get almost similar range 1.19 ± 0.25 . The fibres with runkel ratio below 1 are considered to be thin-walled and have good mechanical properties (Neto et al., 1996; Oluwadare and Sotannde, 2007). The average runkel ratio of P. bourdillonii is lower than that of Ochlandra travancorica (2.44) (Azzini and Zalgado, 1982), G. angustifolia (6.57), G. superba (5.64) (Azzini et al., 1977) D.asper(3.51), D. giganteus (2.37) and B. vulgaris (3.13) (Ciaramello and Azinni, 1971).

_		Radial position		
Height position	Outer	Middle	Inner	Overall
Bottom	8.39 ± 1.08	7.48 ± 1.34	7.33 ± 1.64	7.73 ± 0.74
Middle	7.63 ± 1.05	8.38 ± 1.81	9.11 ± 2.39	8.37 ± 1.00
Тор	9.93 ± 0.91	9.95 ± 1.45	9.60 ± 0.93	9.82 ± 0.60
Overall	8.65 ± 0.6	8.60 ± 0.87	8.68 ± 0.97	8.64 ± 0.47

Table 5. Results of comparison of double wall thickness between height position and between radial position

Between F-value Height position = 1.581^{ns} ; P-value = 0.220Between F-value radial position = 0.002^{ns} ; P-value = 0.998 Interaction between height position and radial position = 0.209^{ns} ; P-value = 0.932

Table 6. Results of comparison of single wall thickness between height position and between radial position

Height position		Overall		
fielght position	Outer	Middle	Inner	- Overan
Bottom	4.20 ± 0.54	3.74 ± 0.67	3.67 ± 0.82	3.87 ± 0.37
Middle	3.82 ± 0.53	4.19 ± 0.91	4.56 ± 1.20	4.19 ± 0.50
Тор	4.96 ± 0.46	4.97 ± 0.72	4.80 ± 0.46	4.91 ± 0.30
Overall	4.33 ± 0.30	4.30 ± 0.44	4.34 ± 0.49	4.32 ± 0.23

Between F-value Height position = 1.581ns; P-value = 0.220Between F-value radial position = 0.002ns; P-value = 0.998 Interaction between height position and radial position = 0.209ns; P-value = 0.932

* Significant at 0.05 level; ns non-significant

Slenderness ratio

The mean slenderness ratio of *P. bourdillonii* is 152.76 ± 4.82 (Table 8). This value is higher than the slenderness ratio of other bamboo species such as *G. angustifolia*(120), *G. superba*(136) (Azzini *et al*, 1977) *D.asper*(136), *D. strictus*(122)(Ciaramello and Azinni, 1971) and *Ochlandra travancorica*(131) (Azzini and Zalgado, 1982). There is an increase in

slenderness ratio from bottom to top. There is no significant difference of slenderness ratio between height position but the slenderness ratio of outer slivers is significantly lower than that of middle and inner slivers. The obtained slenderness ratio of *P. bourdillonii* is higher than *O. abyssinica* 109.98 ± 0.21 (Worku *et al.*, 2023). The fibres extracted from all parts of *P. bourdillonii* have a slenderness ratio greater than 70, indicating their potential to yield high quality sheets suitable for various applications such as packing. The mean slenderness ratio of *P. bourdillonii* exceeds the values obtained for conventional paper making sources *Eucalyptus grandis* (55.18), *Eucalyptus tereticornis* (52.66) and *Eucalyptus camadulensis* (53.33) (Dutt and Tyagi, 2011; Pillai *et al.*, 2013).

T 11 7	D	1.	c	•	C	1 1	· ·	1 4	1 . 1 .	• , •	1	1 /	1 1	• , •
I ahle /	R ACI	ilte o	t com	naricon	ofrun	IZ AL	ratio	hetween	height	nosition	and	hetween	radial	nosition
I aDIC /	. 1103	uns o	i com	parison	UI I UI	I VI	1 atio		neigni	position	anu		1 autai	position
									0	1				1

_		Radial position		Overall
Height position	Outer	Middle	Inner	Overall
Bottom	1.38 ± 0.45	1.05 ± 0.38	1.12 ± 0.53	$1.19^{\rm B}\pm0.25$
Middle	2.00 ± 0.64	1.80 ± 0.79	2.08 ± 0.87	$1.96^{\rm AB}\pm0.41$
Тор	2.87 ± 0.59	2.49 ± 0.77	2.62 ± 0.47	$2.66^{\rm A}\pm0.34$
Overall	2.08 ± 0.34	1.78 ± 0.39	1.94 ± 0.38	1.93 ± 0.21

Between F-value Height position = 4.094^* ; P-value = 0.025Between F-value radial position = 0.174^{ns} ; P-value = 0.841Interaction between height position and radial position = 0.025^{ns} ; P-value = 0.999

* Significant at 0.05 level; ns non-significant Means having different capital letter as superscript differ significantly within a column

Height position		Overall		
freight position	Outer	Middle	Inner	Overan
Bottom	123.19 ± 17.20	158.64 ± 13.87	151.03 ± 13.93	144.29 ± 9.03
Middle	126.36 ± 10.98	171.91 ± 3.89	163.39 ± 6.44	153.89 ± 6.69
Тор	155.76 ± 22.61	152.45 ± 12.18	172.13 ± 12.70	160.11 ± 9.14
Overall	$135.11^{b} \pm 10.18$	$161.00^{a} \pm 6.21$	$162.18^{a} \pm 6.57$	152.76 ± 4.82

 Table 8. Results of comparison of slenderness ratio between height position and between radial position

Between F-value Height position = 1.022^{ns} ; P-value = 0.370Between F-value radial position = 3.764^* ; P-value = 0.033Interaction between height position and radial position = 0.919^{ns} ; P-value = 0.464

* Significant at 0.01 level; ns non-significant, Means having different small letter as superscript differ significantly within a raw

Height position _		Overall		
	Outer	Middle	Inner	= Overall
Bottom	0.49 ± 0.07	0.57 ± 0.06	0.58 ± 0.08	$0.55^{\rm A}\pm0.04$
Middle	0.43 ± 0.08	0.47 ± 0.08	0.46 ± 0.11	$0.45^{AB}\pm0.05$
Тор	0.32 ± 0.06	0.39 ± 0.08	0.39 ± 0.08	$0.36^{\rm B}\pm0.04$
Overall	0.41 ± 0.04	0.48 ± 0.04	0.47 ± 0.05	0.45 ± 0.03
	. 1	D 1 0.004D	F 1 111	

 Table 9. Results of comparison of flexibility ratio between height position and between radial position.

Between F-value Height position = 4.153^* ; P-value = 0.024Between F-value radial position = 0.604ns; P-value = 0.552Interaction between height position and radial position = 0.037ns; P-value = 0.997

Significant at 0.05 level; ns non-significant Means having different capital letter as superscript differ significantly within a column

Table 10. Results of comparison of vessel diameter between height position and between radial position

		0 "		
Height position	Outer	Middle	Inner	Overall
Bottom	75.58 ± 4.21	122.21 ± 6.94	151.95 ± 4.44	116.58 ± 8.87
Middle	80.11 ± 6.20	126.71 ± 3.25	175.65 ± 4.10	127.49 ± 10.72
Тор	83.50 ± 5.52	122.77 ± 8.96	163.10 ± 10.16	123.12 ± 9.79
Overall	$79.73^{\text{c}}\pm3.00$	$123.90^{b}\pm3.68$	$163.56^{a} \pm 4.47$	122.40 ± 5.58

Between F-value Height position = 2.228^{ns} ; P-value = 0.122Between F-value radial position = 129.93^{**} ; P-value < 0.001Interaction between height position and radial position = 0.886^{ns} ; P-value = 0.482

** Significant at 0.01 level; ns non-significant, Means having different small letter as superscript differ significantly within a raw

Flexibility ratio

The flexibility ratio signifies the ease with which fibre interconnects influencing the resultant tensile and bursting strength (David et al., 2016). The observed average flexibility ratio of P. bourdillonii is found to be 0.45 ± 0.03 (Table 9). This was higher than that of Ochlandra travancorica(.29) (Azzini and Zalgado, 1982), D.asper(.22), D. giganteus(.29) and vulgaris(.24) (Ciaramello and В. Azinni. 1971). There is a significant difference in the flexibility ratio of bottom (0.55 \pm 0.04) and top fibres (0.36 ± 0.04) . The flexibility ratio of outer, middle and inner slivers not differ statistically.

Meta xylem vessel diameter

The mean values of bottom, middle and top meta

xylem vessel diameters are $116.58 \pm 8.87 \mu m$, $127.49 \pm 10.72 \mu m$, and $123.12 \pm 9.79 \mu m$ respectively. The average vessel diameter of *P. bourdillonii* is $122.40 \pm 5.58 \mu m$. There is no statistical difference in vessel diameter of the bottom, middle and top positions (Table 10). The size difference of the outer, middle and inner slivers is statistically significant. The outer metaxylem vessels exhibit a lower diameter $79.73\pm 3.00 \mu m$ followed by the middle vessels with a diameter of $123.90 \pm 3.68 \mu m$, while the inner vessels show a higher diameter $163.56 \pm 4.47 \mu m$. This observation aligns with findings of Wahab *et al.* (2010) indicating a progressive increase in vessel diameter from the outer to the inner part of the bamboo culm.

Parenchyma diameter

The parenchyma diameter varies from 39.37 ± 1.47 µm highest at the bottom, 35.58 ± 1.68 µm at the middle and lowest value 34.08 ± 1.59 µm in the top (Table 11). While there is no statistically significant difference between parenchyma diameter among different height positions, a notable contrast observed between outer and inner positions with the outer position has the lowest diameter 32.92 ± 1.78 µm, and inner position displays largest parenchyma diameter 38.86 ± 1.37 µm (P-value < 0.05). Parenchyma diameter of *P. bourdillonii* is higher than 26.6 µm of *Bambusa vulgaris* (Wahab *et al.*, 2009). Fig 9 illustrates Parenchyma of *P. bourdillonii*.



Fig 9. Parenchyma of P.bourdillonii

 Table 11. Results of comparison of parenchyma diameter between height position and between radial position

_	Radial position				
Height position	Outer	Middle	Inner	Overall	
Bottom	36.61 ± 3.50	40.11 ± 2.43	41.38 ± 1.14	39.37 ± 1.47	
Middle	31.52 ± 2.11	37.22 ± 2.88	38.00 ± 3.24	35.58 ± 1.68	
Тор	30.64 ± 3.39	34.41 ± 2.00	37.20 ± 2.35	34.08 ± 1.59	
Overall	$32.92^{b}\pm1.78$	$37.25^{ab}\pm1.46$	$38.86^{a}\pm1.37$	36.34 ± 0.95	

Between F-value Height position = 3.145ns; P-value = 0.055Between F-value radial position = 3.992*; P-value = 0.027Interaction between height position and radial position = 0.084ns; P-value = 0.987

Means having different small letter as superscript differ significantly within a raw

Table 12. Results of comparison	of parenchyma	lumen diameter	between l	height posit	ion and
between radial position					

Height position	Radial position			Overall	
fieight position	Outer	Middle	Inner	- Overall	
Bottom	31.67 ± 2.72	35.40 ± 1.78	35.83 ± 0.97	$34.30^{\rm A}\pm1.16$	
Middle	27.16 ± 2.16	32.60 ± 2.43	33.37 ± 2.47	$31.04^{\mathrm{AB}}\pm1.46$	
Тор	25.93 ± 2.72	29.55 ± 1.40	31.87 ± 1.67	$29.12^{\text{B}} \pm 1.26$	
Overall	$28.25^{\text{b}}\pm1.51$	$32.52^{a} \pm 1.21$	$33.69^{a}\pm1.06$	31.49 ± 0.80	

Between F-value Height position = 4.592^* ; P-value = 0.017Between F-value radial position = 5.486^{**} ; P-value = 0.008Interaction between height position and radial position = 0.122ns; P-value = 0.974

** Significant at 0.01 level; ns non-significant Means having different small letter as superscript differ significantly within a raw, Means having different capital letter as superscript differ significantly within a column

Parenchyma lumen diameter

Parenchyma lumen diameter exhibits a descending trend from the bottom $(34.30\pm 1.16 \ \mu\text{m})$, to the middle $(31.04 \pm 1.46 \ \mu\text{m})$ reaching the lowest value at the top $(29.12 \pm 1.26 \ \mu\text{m})$. significantly, there is a notable statistical significance in parenchyma lumen diameter between the bottom and top positions (Table 12). Moreover, the outer position $(28.25 \pm 1.51 \ \mu\text{m})$ differs statistically from the middle $(32.52 \pm 1.21 \ \mu\text{m})$ and inner position $(33.69 \pm 1.06 \ \mu\text{m})$.

Vascular bundle number / mm²

Middle

Overall

Тор

The results reveal a gradual increase in the mean vascular bundle number per square millimetre with values of, 1.96 ± 0.24 at the bottom, 2.35 ± 0.22 in the middle and 2.75 ± 0.39 at the top. The average vascular bundle /mm² of *P. bourdillonii* is 2.35 ± 0.17 .

Notably there is a statistically significant difference in vascular bundle frequency between bottom and top parts, evidenced by a P-value < 0.05. The difference in vascular bundle frequency of outer, middle, and inner part is statistically significant at 1% level ie, P-value < 0.001 with outer measurements $3.55\pm$ 0.29, middle 1.98 ± 0.14 and top values 1.52 ± 0.13 bundles/mm² (Table 13). This vascular bundle count is higher than the reported values of Bambusa vulgaris by Wahab et al., 2009 G. scortechinii (1.76 bundles/ mm²), G. wrayi (1.44 bundles/mm²) and G. brang (1.37 bundles/mm²) (Mustafa et al., 2011). A high vascular bundle count can serve as an indicator of elevated lignin content which implies stronger material (Mulyaningsih et al., 2022). Average anatomical values are provided in Fig 10.

 $2.35^{AB}\pm0.22$

 $2.75^{\rm A}\pm0.39$

 2.35 ± 0.17

 1.58 ± 0.11

 1.73 ± 0.30

 $1.52^{b} \pm 0.13$



Fig 10. Average anatomical parametes of *P. bourdillonii*; error bars represent mean standard deviation; VD-metaxylem vessel diameter(μ m), PD–parenchyma diameter(μ m), PL-parenchyma lumen diameter(μ m), VB- vascular bundlen/mm².

between radial pos	sition			
Height position -	Radial position			Overall
	Outer	Middle	Inner	- Overall
Bottom	2.99 ± 0.27	1.64 ± 0.29	1.25 ± 0.24	$1.96^{\rm B} \pm 0.24$

 2.05 ± 0.09

 2.26 ± 0.26

 $1.98^b\pm0.14$

 3.41 ± 0.23

 4.26 ± 0.76

 $3.55^{a} \pm 0.29$

Table 13. Results of comparison of vascular bundle number / mm² between height position and between radial position

Between F-value Height position = 4.132^* ; P-value = 0.024 Between F-value radial position =
30.236^{**} ; P-value < 0.001 Interaction between height position and radial position = 0.489 ns; F
value = 0.744

** Significant at 0.01 level; ns non-significant Means having different small letter as superscript differ significantly within a raw, means having different capital letter as superscript differ significantly within a column

	1	1	7 1 1		
Anatomical and fibre	Physical parameters				
parameters	Moisture content	Basic density	Volumetric shrinkage		
Fibre length	-0.132	0.155	-0.146		
Fibre width	-0.103	0.101	-0.107		
Fibre lumen	0.738**	-0.706**	0.706**		
Double wall thickness	-0.897**	0.859**	-0.863**		
Single wall thickness	-0.897**	0.859**	-0.863**		
Runkel	-0.853**	0.845**	-0.825**		
Slenderness ratio	-0.029	0.037	-0.042		
Flexibility ratio	0.844**	-0.807**	0.812**		
Vessel diameter	-0.335	0.509	-0.417		
Parenchyma diameter	-0.574*	0.615*	664**		
Parenchyma lumen	-0.407	0.431	-0.486		
Vascular bundles/mm ²	-0.179	0.083	-0.056		

 Table 14. Correlation of anatomical and fibre parameters with physical properties

** Significant at 0.01 level; * Significant at 0.05 level

Correlation between physical and anatomical properties

The correlation between the physical and anatomical properties of P. bourdilloniiis provided in the Table 14 which indicate a significant inverse correlation between moisture content and key anatomical parameters including fibre wall thickness, runkel ratio and parenchyma diameter. Conversely, there is a noteworthy significant positive correlation between fibre lumen and flexibility ratio with moisture content. All other parameters exhibit non - significant correlation with moisture content. A study by Mohmod et al. (1993) on B. blumeana fibre length and vessel diameter was reported to have a nonsignificant correlation with moisture content. In P. bourdillonii, fibre lumen and flexibility ratio show a significant negative correlation with basic density, while, wall thickness, parenchyma diameter, and runkel ratio show a significant positive correlation to density. The volumetric shrinkage demonstrates a positive and significant correlation with fibre lumen and flexibility ratio and a negative significant correlation with wall thickness, runkel ratio and parenchyma diameter.

The positive significant correlation of basic density with that of fibre wall thickness matches with the findings of Rusch *et al.*, 2019 indicating a direct influence of basic density on fibre wall thickness. This suggest that species with lower density tend to have fibres with thinner walls.

Conclusion

The research focused on examining the physical and anatomical properties of 2-year-old P. bourdillonii along various culm heights. The recorded values of moisture content exhibit a decreasing trend from the bottom to the top of the culm. In contrast, the average basic density of P. bourdillonii shows a reverse trend compared to that of moisture content. The volumetric shrinkage reaches its peak in the middle of the culm. Statistical analysis reveals no significant difference in physical properties across different culm heights. A notable variation is observed between fibre length of the outer and middle parts, with middle slivers showing the highest average value. Fibre width and lumen width of the bottom part exhibit a significant difference compared to middle and top (P < 0.05). However, no significant

difference was observed in wall thickness between height position and radial position. The results indicate that the runkel ratio exceeding 1 and the slenderness ratio is higher than the standard value 70. Anatomical parameters like vessel size, vascular bundle number, parenchyma diameter and lumen were also quantified. Moisture content and shrinkage showed a negative significant correlation with wall thickness, runkel ratio, and parenchyma diameter while showing a positive correlation with fibre lumen and flexibility ratio. Basic density shows a significant positive correlation with wall thickness and parenchyma diameter. Despite the runkel ratio of P. bourdillonii exceeding the recommended threshold, its other parameters such as long fibre length 2.32 ± 0.08 mm and a slenderness ratio greater than 70 (152.76 \pm 4.82) make *P. bourdillonii* suitable for pulping. The two-year age group of Pbourdillonii is less preferred for high-strength demanding purposes due to its higher moisture content and lower basic density when compared to other major bamboo species such as B. bambos and B. balcooa. However, with its non-thorny nature, long internodes, thin culm wall, and aesthetically pleasing golden yellow colour of the culm and culm sheath P. bourdillonii is well suited for handicraft sector.

Acknowledgements

The authors express gratitude to the Director, KFRI, and officials of the Wood Science Technology Department for extending all necessary facilities and support for the present study. We also express sincere gratitude to Dr. Sunanda for extending support for statistical analysis and to officials of the Kerala forest department for providing necessary support for the fieldwork. The first author expresses sincere gratitude to CSIR-UGC for providing financial support.

Reference

- Abd. Latif Mohmod, A.L.M. and Mohd. Tamizi Mustafa, M.T.M., 1992. Variation in anatomical properties of three Malaysian bamboos from natural stands.
- Adi, D.S., Risanto, L., Damayanti, R., Rullyati, S., Dewi, L.M., Susanti, R., Dwianto, W., Hermiati, E. and Watanabe, T., 2014. Exploration of unutilized fast growing wood species from secondary forest in Central Kalimantan: Study on the fiber characteristic and wood density. *Procedia Environmental Sciences*, 20, pp.321-327. https://doi.org/10.1016/j.proenv.2014. 03.040

- Ahmad, Z., Upadhyay, A., Ding, Y., Emamverdian, A. and Shahzad, A., 2021. Bamboo: Origin, habitat, distributions and global prospective. Biotechnological Advances in Bamboo: The "Green Gold" on the Earth, pp.1-31. https:// doi.org/10.1007/978-981-16-1310-4_1
- Anokye, R., Kalong, R.M., Bakar, E.S., Ratnasingam, J., Jawaid, M. and Awang, K., 2014. Variations in moisture content affect the shrinkage of Gigantochloa scortechinii and Bambusa vulgaris at different heights of the bamboo culm. *BioResources*, 9(4), pp.7484-7493.
- ASTM (American Society for Testing and Materials). 1997. Standard methods of testing small clear specimens of timber. Annual Book of ASTM Standards Des. ASTM D143-94 (Reap proved 1997) Vol. 4.10. Philadelphia, PA.
- Azzini, A., Ciaramello, D. and Nagai, V., 1977. Densidade básica e dimensões das fibras em bambus do gênero Guadua. *Bragantia*, 36, pp.1-6.
- AZZINI, A. and SALGADO, A., 1982. Bambu e suas possibilidades industriais. In CONGRESSO ANUAL DA ASSOCIAÇÃO BRASILEIRA DE CELULOSE E PAPEL (Vol. 15, pp. 205-224).
- Boadu, K.B., Ansong, M., Afrifah, K.A. and Nsiah-Asante, E., 2022. Pulp and paper making characteristics of fibers from plantation-grown Oxythenantera abyssinica and Beema bamboo (a tissue cultured clone from Bambusa balcooa). Journal of Natural Fibers, 19(11), pp.4198-4209. https:// doi.org/10.1080/15440478.2020.1856270
- King, C. and Wu, J., 2021. Trade Overview 2019: Bamboo and rattan commodities in the international market. *INBAR Trade Reports*.
- Nogueira, J.S., 2019. Estratégias para a conservação ex situ de Dendrocalamus asper e micropropagação de espécies do gênero Guadua (Bambusoideae, Poaceae).
- David-Sarogoro, N. and Emerhi, E.A., 2016. Runkel, flexibility and slenderness ratios of Anthocleista djalonensis (A) wood for pulp and paper production. *African Journal of Agriculture, Technology and Environment*, 5(2), pp.27-32.
- Dutt, D. and Tyagi, C.H., 2011. Comparison of various eucalyptus species for their morphological, chemical, pulp and paper making characteristics.
- Egbewole, Z.T., Rotowa, O.J. and Omoake, P.O., 2015. Evaluation of fibre quality of Bambusa vulgaris (Bamboo) as a raw material for pulp and paper production. *PAT*, *11*(2), pp.188-202.

- Forest Survey of India (FSI), 2019. Indian State of Forest Report 2019. Dehradun -248195, Uttarakhand, India.
- Franklin, G.L., 1945. Preparation of thin sections of synthetic resins and wood-resin composites, and a new macerating method for wood. *Nature*, 155(3924), pp.51-51.
- Hamdan, H., Nordahlia, A.S., Anwar, U.M.K., Iskandar, M.M., Omar, M.M. and K, T., 2020. Anatomical, physical, and mechanical properties of four pioneer species in Malaysia. *Journal of Wood Science*, 66, pp.1-9.
- INBAR, 2019. Trade Overview 2018: Bamboo and Rattan Commodities in China. Beijing 100102, China.
- INBAR, 2019a. Trade Overview 2017: Bamboo and Rattan Commodities in the International Market. pp. 32.
- IS: 6874 2008, Indian standard method of tests for bamboo. First revision
- Jane, F.W., 1933. The microscopic examination of woody materials. *Watson's microscopic record*, (30), pp.1-9.
- Kamruzzaman, M., Saha, S.K., Bose, A.K. and Islam, M.N., 2008. Effects of age and height on physical and mechanical properties of bamboo. *Journal of Tropical Forest Science*, pp.211-217.
- Kayama, T., 1979. Pulping and papermaking properties and wood properties of tropical hardwoods.
- Kumar, M.S.M., 2009. Revisionary studies on four genera of Indian bamboos. Kerala Forest Research Report, Kerala, India.
- Liese, W., 1998. *The anatomy of bamboo culms* (Vol. 18). Brill.
- Surendranath, C., 2004. Constraints in sustainable development: a case study of inter-sectoral allocation of bamboo & reed resources in Kerala. *Kerala Research Programme on Local Level Development*.
- Maya, C. and Pandey, C. N. 2013. A Study on anatomical and physical properties of cultivated bamboo (Oxytenanthera monostigama). *International Journal* of Current Science. 62-66.
- Megra, M.B., Bachheti, R.K., Tadesse, M.G. and Worku, L.A., 2022. Evaluation of pulp and papermaking properties of Melia azedarach. *Forests*, 13(2), p.263.
- Mohmod, A.L., Amin, A.H., Kasim, J. and Jusuh, M.Z., 1993. Effects of anatomical characteristics on the physical and mechanical properties of Bambusa blumeana. *Journal of Tropical Forest Science*, pp.159-170.

- Mulyaningsih, T., Karnika, D.A. and Muspiah, A., 2022. Comparison of stem anatomy of Bambusa vulgaris Schrad and Schizostachyum brachycladum (Kurz) Kurz (Poaceae) in Lombok. *Advances in Bamboo Science*, *1*, p.100010. https://doi.org/10.1016/ j.bamboo.2022.100010
- Mussa, M., Desalegn, G., Kaba, G. and Tesfaye, A., 2023. Physical and Chemical Properties of Highland Bamboo (Yushania alpina) Culms Grown in Ethiopia. Drvna industrija, 74(3), pp.287-296. https:// doi.org/10.5552/drvind.2023.0059
- Mustafa, M.T., Wahab, R., Sudin, M., Sulaiman, O., Kamal, N.A.M. and Khalid, I., 2011. Anatomical and microstructures features of tropical bamboo Gigantochloa brang, G. levis, G. scotechinii and G. wrayi.
- Navaee-Ardeh, S., Mohammadi-Rovshandeh, J. and Pourjoozi, M., 2004. Influence of rice straw cooking conditions in the soda–ethanol–water pulping on the mechanical properties of produced paper sheets. *Bioresource Technology*, 92(1), pp.65-69. https://doi.org/10.1016/j.biortech.2003.07.006
- Neto, C.P., Seca, A., Fradinho, D., Coimbra, M.A., Domingues, F., Evtuguin, D., Silvestre, A. and Cavaleiro, J.A.S., 1996. Chemical composition and structural features of the macromolecular components of Hibiscus cannabinus grown in Portugal. *Industrial Crops and Products*, 5(3), pp.189-196. https://doi.org/10.1016/0926-6690(96)89448-9
- Oluwadare, A.O. and Sotannde, O.A., 2007. The relationship between fibre characteristics and pulp-sheet properties of Leucaena leucocephala (Lam.) De Wit. *Middle-East journal of scientific research*, 2(2), pp.63-68.
- Pillai, P.C., Pandalai, R.C., Dhamodaran, T.K. and Sankaran, K.V., 2013. Effect of silvicultural practices on fibre properties of Eucalyptus wood from shortrotation plantations. *New Forests*, 44, pp.521-532. https://doi.org/10.1007/s11056-012-9360-6
- Razak Wahab, M.T.M., Rahman, S., Salam, M.A., Sulaiman, O., Sudin, M. and Rasat, M.S.M., 2006. RELATIONSHIP BETWEEN PHYSICAL, ANA-TOMICAL AND STRENGTH PROPERTIES OF 3-YEAR-OLD CULTIVATED TROPICAL BAMBOO Gigantochloa scortechinii.
- Rusch, F., Ceolin, G.B. and Hillig, É., 2019. Morphology, density and dimensions of bamboo fibers: a bibliographical compilation. https://doi.org/10.1590/1983-40632019v4955007

Rusch, F., Wastowski, A.D., de Lira, T.S., Moreira, K.C.C.S.R.

and de Moraes Lúcio, D., 2023. Description of the component properties of species of bamboo: a review. *Biomass Conversion and Biorefinery*, *13*(3), pp.2487-2495. https://doi.org/10.1007/s13399-021-01359-3

- Sadiku, N.A., Oluyege, A.O. and Ajayi, B., 2016. Fibre dimension and chemical characterisation of naturally grown Bambusa vulgaris for pulp and paper production. Journal of Bamboo & Rattan (Kerala Forest Research Institute), 15.
- Seethalakshmi, K.K., Kumar, M.M., Pillai, K.S. and Sarojam, N., 1998. Bamboos of India: A compendium (Vol. 17). Brill.
- Selvan, R.T., Parthiban, K.T. and Khanna, S.U., 2017. Physio-chemical properties of bamboo genetic resources at various age gradations. *Int. J. Curr. Microbiol. Appl. Sci*, 6, pp.1671-1681. https:// doi.org/10.20546/ijcmas.2017.609.205
- Sharma, A.K., Dutt, D., Upadhyaya, J.S. and Roy, T.K., 2011. Anatomical Morphological, and chemical characterization of <u>bambusa tulda, dendrocalamus Hamiltonii, Bambusa Balcooa, Malocana Baccifera, Bambusa Arundinacea, and Eucalypyus Tereticornis.</u> BioResources, 6(4).
- Singh, O., 2008. Bamboo for sustainable livelihood in India. *Indian Forester*, 134(9), pp.1193-1198.
- Sugesty, S., Kardiansyah, T. and Hardiani, H., 2015. Bamboo as raw materials for dissolving pulp with environmental friendly technology for rayon fiber. *Procedia Chemistry*, 17, pp.194-199. https:// doi.org/10.1016/j.proche.2015.12.122
- Vetter, R.E., Sá Ribeiro, R.A., Sá Ribeiro, M.G. and Miranda, I.P., 2015. Studies on drying of imperial bamboo. *European Journal of Wood and Wood Products*, 73, pp.411-414. https://doi.org/10.1007/s00107-015-0900-6
- Viana, L.C., Trugilho, P.F., Hein, P.R.G., Lima, J.T. and da Silva, J.R.M., 2009. Predicting the morphological characteristics and basic density of Eucalyptus wood using the NIRS technique. *Cerne*, 15(4), pp.421-429.
- Villareal, J.F., Marasigan, O.S., Mendoza, R.C., Alipon, M.A. and Abasolo, W.P., 2020. Morphological, Anatomical, and Physical Properties of Iron Bamboo (Guadua angustifolia Kunt.) Grown in the Philippines. *Philippine Journal of Science*, 149.
- Wahab, R., Mohamed, A., Mustafa, M.T. and Hassan, A., 2009. Physical characteristics and anatomical properties of cultivated bamboo (Bambusa vulgaris Schrad.)

culms. *Journal of Biological Sciences*, 9(7), pp.753-759.

- Wahab, R., Mustapa, M.T., Sulaiman, O., Mohamed, A., Hassan, A. and Khalid, I., 2010. Anatomical and physical properties of cultivated two-and four-yearold Bambusa vulgaris. *Sains Malaysiana*, 39(4), pp.571-579.
- Worku, L.A., Bachheti, A., Bachheti, R.K., Rodrigues Reis, C.E. and Chandel, A.K., 2023. Agricultural residues as raw materials for pulp and paper production: overview and applications on membrane fabrication. *Membranes*, 13(2), p.228. https:// doi.org/10.3390/membranes13020228
- Worku, L.A., Bachheti, R.K., Tadesse, M.G. and Bachheti, A., 2023. Proximate chemical analysis and effect of age and height of Oxytenanthera abyssinica on fiber morphology and chemical compositions for pulp and paper production potential. *International Journal of Polymer Science*, 2023(1), p.5582854.https://doi.org/10.1155/2023/5582854
- Xu, C.Y., Wang, H.X., Zhang, X.Y., Fu, S.Y. and Wu, J.E., 2006. Lignocellulose selectivity degradation of white rot fungi in bamboo. *J microbiol*, 26, pp.14-18.
- Zhan, H., Tang, G.J., Wang, C.M. and Wang, S.G., 2015. Chemical properties and fiber morphology of Fargesia fungosa at different culm ages and heights. *BioResources*, 10(3), pp.5666-5676.